

TEST REPORT

Mechanical & Hardgoods Laboratory

Report No. : YA30049/2019

Page : 1 of 2

Date : MAR. 27, 2019

Pro-Sight Optical Co., LTD

NO.30, Ln.9, Fude St., Luzhu Dist., Kaohsiung 82146, TAIWAN

The following merchandise was submitted and identified by the applicant as:

Product Description: Decentered 8C*90 mm+Anti-fog

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested: EN 166:2001 Personal eye-protection – Specifications
Clause 7.3.1 Resistance to surface damage by fine particles (K)
Clause 7.3.2 Resistance to fogging of oculars (N)

Test Method & Result: --- See following sheet(s) ---

Date of Receipt: MAR. 18, 2019

Testing Period: MAR. 18 ~ 27, 2019

--- See Next Page ---

Signed for and on behalf of
SGS Taiwan Ltd.


Owen Cheng
Manager



Laboratory address:
61, Kai-Fa Road, Nanzih Export Processing Zone, 81170, Kaohsiung, Taiwan

TEST REPORT

Mechanical & Hardgoods Laboratory

Report No. : YA30049/2019

Page : 2 of 2

Test Method & Result:

EN 166:2001 Personal eye-protection – Specifications

Clause

7.3.1 Resistance to surface damage by fine particles (K)

Result

Pass

Finding

Sample	Maximum value of the reduced luminance factor	Test Value[(cd/m ²)/lx]
01	5 (cd/m ²)/lx	3.64
02		3.26

7.3.2 Resistance to fogging of oculars (N)

Pass

Finding

The assessed samples were free from fogging for a minimum of 8 seconds.

– Picture(s) –




Photo "A" Appearance of sample

--- End of Report ---